

### **DELO-MONOPOX® 6093**

#### **Base**

- epoxy casting resin
- one-part, heat curing, not filled

#### **Use**

- for casting, coating and mounting of components and modules
- especially for use in the electronic industry
- good flowing behaviour

#### **Processing**

- to heat components, higher temperatures can also be used
- the heating time for components has to be added to the actual curing time
- for curing, the inside of the adhesive layer has to have the required temperature
- development of an exothermal reaction heat depends on the adhesive quantity used thus, overheating may occur, in this case the curing temperature has to be reduced accordingly
- the resin is supplied ready-to-use and best applied from the original container or with DELO dispensing units
- surfaces to be bonded should be dry, free from dust, grease and other contaminants
- DELOTHEN cleaners are recommended for cleaning
- adherence can be improved by sand-blasting, grinding or pickling

#### **Curing**

- at temperatures between +100 and +130 °C
- higher temperatures accelerate, lower temperatures prolong curing process and may change the properties of cured product

#### **Technical data**

Color	black
Density [g/cm <sup>3</sup> ] at room temperature (approx. 23 °C)	1.2
Viscosity [mPas] at 23 °C, Brookfield sp/r 7/5	40000
processing time at room temperature (approx. 23 °C)	6 weeks
Curing time until final strength [min] at +130 °C	30
Tensile shear strength Al/Al [MPa] DIN EN 1465, sand-blasted join part thickness: 1.6 mm after 30 min at +130 °C	14

DELO Industrial Adhesives  
DELO-Allee 1 · D-86949 Windach  
Phone +49 8193 9900-0  
Fax +49 8193 9900-144  
E-Mail [info@DELO.de](mailto:info@DELO.de) · [www.DELO.de](http://www.DELO.de)

compression/shear strength PETP/PETP [MPa] standard DELO 5 after 30 min at +100 °C	20
compression/shear strength PS/PS [MPa] standard DELO 5 after 30 min at +100 °C	26
tensile strength [MPa] DIN EN ISO 527, after 30 min at +130 °C	41
elongation at tear [%] DIN EN ISO 527, after 30 min at +130 °C	1.6
Young modulus [MPa] DIN EN ISO 527, after 30 min at +130 °C	2900
shore hardness D DIN 53505, after 30 min at +100 °C	74
indentation hardness [MPa] ISO 2039, part 1	137
glass transition temperature [°C] rheometer	93
coefficient of elongation [ppm/K] TMA, in a temperature range of +25 to +140 °C	111
coefficient of elongation [ppm/K] TMA, in a temperature range of +30 to +70 °C	59
coefficient of elongation [ppm/K] TMA, in a temperature range of +110 to +160 °C	183
shrinkage [vol. %] standard DELO 13	1.1
water absorption [weight %] DIN EN ISO 62, after 30 min at +100 °C	0.1
chemical stability	good
Recommended long-term temperature range of use [°C]	-40 to 130
temperature resistance [°C]	+240
Specific volume resistance [ $\Omega$ cm] VDE 0303, part 3, after 45 min at +130 °C	2.9xE15
surface resistance [ $\Omega$ ] VDE 0303, part 3, after 45 min at +130 °C	7.0xE12
Dielectric strength [kV/mm] VDE 0303, part 2, after 45 min at +130 °C	18.1
Dielectric constant VDE 0303, part 4, after 45 min at +130 °C	3.9
creep resistance CTI VDE 0303, part 1, IEC 112, after 45 min at +130 °C	100 M
Storage life at approx. +5 °C in unopened original container	6 months

## **Instructions and advice**

### **General**

The data and information provided are based on tests performed under laboratory conditions. Reliable information about the behaviour of the product under practical conditions and its suitability for a specific purpose cannot be concluded from this.

It is the user's responsibility to test the suitability of the product for the intended purpose by considering all specific requirements. Type and physical and chemical properties of the materials to be processed with the product, as well as all actual influences occurring during transport, storage, processing and use, may cause deviations in the behaviour of the product compared to its behaviour under laboratory conditions. All data provided are typical average values or uniquely determined parameters measured under laboratory conditions.

The data and information provided are therefore no guarantee for specific product properties or the suitability of the product for a specific purpose.

### **Instructions for use**

The instruction for use is available under following address: [www.DELO.de](http://www.DELO.de). If requested we will also be pleased to send it to you.

### **Occupational health and safety**

see material safety data sheet

### **Specification**

see quality assurance test report